# **3M**Ultra High Temperature Double Coated Tape 9077

Technical Data	November 2006
recillical Data	November 2006

#### **Product Description**

 $3M^{\text{TM}}$  Ultra High Temperature Double Coated Tape 9077 utilizes a high performance and low outgassing adhesive system having excellent heat resistance in high temperature environments. This adhesive system has excellent holding power and much higher adhesion strength at high temperatures than typical pressure sensitive adhesive tapes.

3M™ Ultra High Temperature Double Coated Tape 9077 is a double coated non-woven adhesive tape with improved die-cut and converting performance.

Note: If a double coated tape is needed, please refer to the  $3M^{TM}$  Adhesive Transfer Tape 9079 technical data page.

#### Construction

Adhesive Type	Release Liner	Color
0.002 in. (0.05 mm) thick Double coated non-woven high temperature acrylic adhesive	0.0036 in. (0.09 mm) thick heat resistant liner	Clear

#### **Features**

- High temperature release liner that is able to survive from a typical lead-free solder reflow process having a peak temperature up to 500°F (260°C).
- Ideal for Flexible Printed Circuit (FPC) attachments in many areas of electronics subjected to high temperature processing and operating environments.
- Releasable after lead-free solder reflow.
- High adhesion, excellent holding power and low outgas.

## **3M<sup>™</sup> Ultra High Temperature Double Coated Tape** 9077

#### Performance Characteristics

Note: The following technical information and data should be considered representative or typical only, and should not be used for specification purposes.

 $3M^{\text{TM}}$  Ultra High Temperature Double Coated Tape 9077 is made from a high temperature acrylic adhesive system, and will become softer as temperature increases and firmer as temperature decreases. As the adhesive becomes firmer, the adhesion performance generally increases. At low temperatures (lower than -40°F[-40°C]), the tapes become very firm and glassy; the ability to absorb impact energy is reduced.

Adhesive strength and liner release performance before and after a typical lead-free solder reflow are presented here along with static shear data a high temperatures.

- 1. 90° Peel Adhesion to Various Surfaces (per ASTM D3330)
  - Pull Tab: 0.003 in. (75 μm) thick Copper Clad Laminate (or flexible circuit)
  - Bonded samples were dwelled at room temperature for 20 to 40 minute
  - Peel speed at 12 in./min. (or 300 mm/min.) at room temperature
  - Solder reflow peak temperature: 500°F (260°C) for 40 seconds

Solder Reflow Effect	Before Reflow	After Reflow
Polyimide Film	5.31 lb./in.	2.91 lb./in.
	(9.3 N/cm)	(5.1 N/cm)
Glass Epoxy	6.28 lb./in.	5.19 lb./in.
	(11 N/cm)	(9.1N/cm)
Polyester Film	N/A	N/A

### 3M<sup>™</sup> Ultra High Temperature Double Coated Tape

#### 9077

Performance Characteristics (continued) Note: The following technical information and data should be considered representative or typical only, and should not be used for specification purposes.

- 2. Static Shear (Creep or Slippage Testing)
  - Overlap area: 1 in. x 1 in. (or 25 mm x 25 mm).
  - 1 hour dwell time to stainless steel at 212°F (100°C) and 356°F (180°C), respectively.
  - Measure the slippage length after 1 hour with a holding weight of 3.3 pounds (1.5 kg).

212°F (100°C)	No slippage
356°F (180°C)	0.008 in. (0.2 mm)

- 3. 90° LinerRelease
- Peel off liner at 90° angle.
- Peel speed at 12 in./min. (or 300 mm/min.) at room temperature.
- Solder reflow peak temperature and duration time: 500°F (260°C) for 20 to 40 seconds.

Before Reflow	29grams/in. (0.11 N/cm)
After Reflow	39 grams/in. (0.15 N/cm)

#### **Application Techniques**

Bond strength is dependent upon the amount of adhesive-to-surface contact developed. Firm application pressure helps develop better adhesive contact and improves bond strength.

To obtain optimum adhesion, the bonding surfaces must be clean, dry, and well unified. Some typical surface cleaning solvents are isopropyl alcohol/water mixture or heptane.\*

Ideal tape application temperature range is  $70^{\circ}F$  to  $100^{\circ}F$  ( $21^{\circ}C$  to  $38^{\circ}C$ ). Initial tape application to surfaces at temperatures below  $50^{\circ}F$  ( $10^{\circ}C$ ) is not recommended because the adhesive becomes too firm to adhere readily. However, once properly applied, low temperature holding is generally satisfactory.

\*Note: When using solvents, extinguish all ignition sources and follow the manufacturer's precautions and directions for use.

## **3M<sup>™</sup> Ultra High Temperature Double Coated Tape** 9077

Available Sizes	Standard Length:	109.3 yds. (100 m)	
	Standard Width:	19.6 in. (500 mm)	
	Normal Slitting Tolerance:	± 1/32 in. (0.8 mm)	
Storage	Store under normal conditions of 70°F (21°C) and 50% relative humidityin the original carton.		
ShelfLife	To obtain best performance, use this product within 12 months from date of manufacture.		
Technical Information	The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.		
Product Selection and Use	Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product and appropriate safety products, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property.		
Warranty, Limited Remedy And Disclaimer	Unless a different warranty is specifically stated on the applicable 3M product packaging or product literature (in which case such warranty governs), 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OFACOURSEOFDEALING, CUSTOM, OR USAGEOFTRADE. If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.		

ept for the limited remedy stated above, and except to the extent prohibited by law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.



 $This Industrial Adhesives and Tapes Division\ product\ was\ manufactured\ under\ a\ 3M\ quality\ system\ registered\ to\ ISO\ 9001\ standards$ 



Industrial Adhesives and Tapes Division Converter Markets 3M Center, Building 225-3S-06 St. Paul, MN 55144-1000 800-362-3550 www.3M.com/converter

3M is a trademark of 3M Company. ©3M 2018 E 70-0713-4678-0